



FP200
10/12/2005

M A T E R I A L S A F E T Y D A T A S H E E T

PRODUCT NAME: FLEX-PATCH SMOOTH / WHITE
PRODUCT CODE: FP200

HMIS CODES: H F R P
1*0 0 J

===== SECTION I - MANUFACTURER IDENTIFICATION =====

MANUFACTURER'S NAME: Textured Coatings of America
Corporate & East Plant Address: 2422 East 15th Street, Panama City, FL 32405
West Coast Plant: 5950 S. Avalon Blvd. Los Angeles, CA 90003

EMERGENCY PHONE : 800-424-9300 DATE PRINTED : 10/12/2005
INFORMATION PHONE : 850-769-0347 NAME OF PREPARER : Akiko Lovan

===== SECTION II - HAZARDOUS INGREDIENTS/SARA III INFORMATION =====

REPORTABLE COMPONENTS	CAS NUMBER	WEIGHT PERCENT
CRYSTALLINE SILICA QUARTZ OSHA PEL: 5 MG/M3, ACGIH TLV: 5 MG/M3	14808-60-7	3.48
Perlite OSHA PEL: 5 MG/M3, ACGIH TLV: 5 MG/M3	93763-70-3	5
Diatomaceous Earth.silica OSHA PEL: .075 MG/M3	68855-54-9	<5
Titanium dioxide OSHA PEL: 15MG/M3, ACGIH TLV: 10MG/M3, OTHER: DUST	13463-67-7	<5
TRIMETHYL PENTANEDIOL MONOISOBUTYRATE OSHA PEL: N.E., ACGIH TLV: N.E.	25265-77-4	<5
OCTYLPHENOXYPOLYETHOXYETHANOL OSHA PEL: N.A, ACGIH TLV: N.A	9036-19-5	<5
* ETHYLENE GLYCOL OSHA PEL: 50PPM, ACGIH TLV: 50PPM	107-21-1	1

* Indicates toxic chemical(s) subject to the reporting requirements of section 313 of Title III and of 40 CFR 372.

===== SECTION III - PHYSICAL/CHEMICAL CHARACTERISTICS =====

BOILING RANGE: 387 deg F - 471 deg F SPECIFIC GRAVITY (H2O=1): 1.12
VAPOR DENSITY: HEAVIER THAN AIR EVAPORATION RATE: SLOWER THAN ETHER
COATING V.O.C.: 0.35 lb/gallon MATERIAL V.O.C.: 0.2 lb/gallon
SOLUBILITY IN WATER: Non Soluble
APPEARANCE AND ODOR: Fruity odor. Clear, light yellow liquid.

EMERGENCY AND FIRST AID PROCEDURES

In the case of ingestion and if medical care will be delayed several hours, use three to four 1-oz shots of 86 proof whiskey for a source of ethyl alcohol before or during transport.

===== SECTION VII - PRECAUTIONS FOR SAFE HANDLING AND USE =====

STEPS TO BE TAKEN IN CASE MATERIAL IS RELEASED OR SPILLED

Eliminate ignition sources, provide good ventilation, dike spill area and add absorbent earth or sawdust to spilled liquid. Thoroughly wet w/ water and mix.

WASTE DISPOSAL METHOD

Collect absorbent/water/spilled liquid mixture into metal containers and add enough water to cover. Consult local, state & federal hazardous waste regulation before disposing into approved hazardous waste landfills. Obey relevant laws.

PRECAUTIONS TO BE TAKEN IN HANDLING AND STORING

Use non-sparking utensils when handling this material. Avoid hot metal surface. Use in cool, well-ventilated areas. Keep containers closed when not in use. Keep away from excessive heat and open flames.

OTHER PRECAUTIONS

Smoking in area where this material is used should be strictly prohibited. Tools used with this material should be made from aluminum, brass or copper. Plastic utensils should not be used.

===== SECTION VIII - CONTROL MEASURES =====

RESPIRATORY PROTECTION

When spraying this material use a NIOSH approved cartridge respirator or gas mask suitable to keep airborne mists and vapor concentrations below the time weighted threshold limit values. When using in poorly ventilated and confined spaces, use a fresh-air supplying respirator or a self-contained breathing apparatus.

VENTILATION

General mechanical ventilation or local exhaust should be suitable to keep vapor concentrations below TLV. Ventilation equipment must be explosion proof.

PROTECTIVE GLOVES: Impermeable chemical handling gloves for skin protection.

EYE PROTECTION: Use chemical safety glasses, goggles, and face shields for eye protection.

OTHER PROTECTIVE CLOTHING OR EQUIPMENT

Use impermeable aprons and protective clothing whenever possible to prevent skin contact. The use of head caps whenever possible is strongly recommended.

WORK/HYGIENIC PRACTICES: Eye washes and safety showers in the workplace are recommended.

===== SECTION IX - DISCLAIMER =====

To the best of our knowledge, the information contained herein is accurate, obtained from sources believed by Textured Coatings of America, Inc. to be accurate.